



Applications

- Welding electrodes
- Refractory bricks
- Pyrotechnics

Form

Flaked and/or chipped

For more detailed information, please contact:

Luxfer Magtech
2590 Ridgeway Blvd.
Manchester, NJ 08759
United States

LMD-Magnesium@Luxfer.com
+1 855 LUXFER1
www.luxfermagtech.com

Copyright © Luxfer Magtech 2020.
All rights reserved.

Magnesium Aluminum Powders for Commercial Applications

Magnesium aluminum powders are manufactured to the highest standards using state-of-the-art equipment and highly engineered processes. Our ability to control particle size and to reproduce particle size distributions from drum-to-drum and lot-to-lot sets us apart in the metal powders industry. Short lead-times allow us to react quickly to our customers' changing demands.

Standard Granulations

Nominal Mesh Size	Nominal Micron Size
-35 mesh	-500 μm
-100 mesh	-150 μm
-200 mesh	-75 μm
-325 mesh	-45 μm

*Custom particle size distributions available.

Chemical Composition

Magnesium	50.0 \pm 2.0%
Aluminum	50.0 \pm 2.0%