



## Applications

- Small caliber ammunition
- Pyrotechnics
- Tracer Rounds
- Other specialty applications

## Specification

JAN-M-454 Type A

## Form

Flaked and/or chipped

## Standard Granulation

- Passing 100-mesh: 99.5% min.
- Passing 120-mesh: 98% min.
- Passing 230-mesh: 45-65%

For more detailed information, please contact:

Luxfer Magtech  
2590 Ridgeway Blvd.  
Manchester, NJ 08759  
United States

LMD-Magnesium@luxfer.com  
+1 855 LUXFER1  
www.luxfermagtech.com

Copyright © Luxfer Magtech 2020.  
All rights reserved.

# Magnesium Aluminum Powders for Military Applications

Luxfer Magtech produces magnesium-aluminum powders for a variety of applications to support the U.S. Army, Navy, Air Force, and allied governments. Magnesium Aluminum powders are manufactured to the highest standards using state-of-the-art equipment and highly engineered processes.

Our ability to control particle shape and size and to reproduce particle size distributions and particle morphology from drum-to-drum and lot-to-lot sets us apart in the metal powders industry. Short lead-times allow us to react quickly to our customers' changing demands.

## Chemical Composition

Magnesium	50.0 ± 2.0%
Aluminum	50.0 ± 2.0%
Total magnesium and aluminum (min.)	98.0%
Oxides	2.0%
Iron (max.)	0.75%
Silicon (max.)	0.5%
Other metals (max.)	0.5%
Zinc (max.)	0.1%
Grease and fats (max.)	0.01%
Moisture (max.)	0.05%
Grit (max.)	0.1%